

Schedule of Product Compatibility and Recommended Dry Times

WOOD KOTE PRODUCTS INC

The schedule below is intended to offer a guideline for the amount of time required (in hours) between applications of products. The times are calculated at 68-72°F (20-22°C) at sea level and at 40-50% relative humidity. Required dry times will increase with lower temperatures and/or higher elevation and/or humidity.

Find the subject product in the column titled CURRENT PRODUCT. Then continue along that row from left to right until the column of the subsequent product in the row titled SUBSEQUENT PRODUCT intersects. Where there is a specified dry time in the intersecting cell, it is only an indication that it is possible to apply the subsequent product over the current and should not be interpreted as a recommendation. Products that should not be applied over the current product are indicated with NR (Not Recommended). Products that should never be applied over the current product are indicated with DNA (Do Not Apply).

		Lite-N-Up	WoodPerfect	W-F-C	Jel'd Stain	Ultra Flagship UV 450	MetaKote
PRODUCT PRODUCT	Lite-N-Up	1	72	72	72	72	72
	WoodPerfect	DNA	1	DNA	12	12	12
	W-F-C	DNA	DNA	1	DNA	12	12
	Jel'd Stain	DNA	24	DNA	NR	4	8
	Ultra Flagship UV 450	DNA	DNA	DNA	8	8	NR
	MetaKote	DNA	DNA	DNA	8	8	8*

*MetaKote: Allow 24 hours before recoating on non-wood surfaces.